

## **Analytical Chemistry Technique to "Preparation, Characterization & Antibacterial Evaluation of Silver Nanoparticles from extract Medicinal Plant"**

**H. N. K. AL-Saman**

*Department of Pharmaceutical Chemistry, College of Pharmacy, University of Basrah, Iraq, hussein.khalf@uobasrah.edu.iq*

**Mazin A.A. Najm**

*Pharmaceutical chemistry Department, College of Pharmacy, Al-Ayen University, Thi-Qar, Iraq.*

**Majid Jabir**

*University of Glasgow/UK, University of Technology, Iraq.*

**Hussein H. Hussein**

*Department of Pharmaceutical Chemistry, College of Pharmacy, University of Basrah, Iraq.*

**Falah Hassan Shari**

*Department of Clinical Laboratory Sciences, College of Pharmacy, University of Basrah, Iraq.*

### **Abstract**

"AIM"- This project aims to make silver nanoparticles from extract medicinal plants, describe them, and test their antibacterial efficacy. "MATERIAL & METHODS" Fresh "Shafallah tree" or other name A. scholaris "Devil tree" leaves free of infection obtained from various places. To release intracellular chemicals into solution, heat the mixture at 60° C for 15 minutes while stirring constantly. This sample must be chilled and filtered using simple filter paper with Whatman No. 1 filter paper, then freeze at 4° C and utilized to manufacture biogenic silver nanoparticles. 10 mL of A. scholaris plant component extracts "leaves, foliage, and fruits" have been given one by one to a 250 mL conical flask containing 100 mL 5mM silver nitrate solution. The AgNO<sub>3</sub> solution is originally whitish in color, but after being swirled constantly for 30 to 60 minutes at room temperature (30 °C), the hue changed from whitish to brownish orange, visibly confirming the creation of biogenic silver nanoparticles. The employment of NaCl as a suspending electrolyte arrangement is used to analyze the initial weakening of the nanoparticles' fluid response (5mL) with twice refined water "50 mL" "2 x10<sup>-2</sup> M NaCl". The needed pH cost is then altered at that moment.- "RESULTS"- The green amalgamation of silver nanoparticles is performed using pre-arranged various plant components. According to the inscription, the silver nanoparticle arrangement is shaded from dull brown to blackish. The color altered from colorless to brownish orange to blackish after adding A. scholaris leaf extracts to AgNO<sub>3</sub> solution, indicating AgNPs production. "CONCLUSION"-According to the study, AgNPs antibacterial action is thought to be due to its positive charge. The concentration of biogenic AgNO<sub>3</sub> determines their antibacterial efficacy against Gram-negative bacteria.

**Keywords:** *"analytical Chemistry Technique", Antibacterial Evaluation, Silver Nanoparticles, Medicinal Plant.*

## INTRODUCTION

Metal nanoparticles have been used from the beginning of time. Thousands of years ago, individuals in Mesopotamia in the ninth century were the first to apply nanoparticles without understanding their science. Painting copper and silver salt with vinegar and ochre on top of pottery and then heating it to generate beautiful metallic glitter is used by the artists in this project. Since Roman times, people have used colloidal gold and silver to dye a vibrant yellow, pink, or mauve hue, depending on their familiarity with the metals. [1,2]. The term "nano" comes from a Greek phrase that means "one billionth of a dimension." Half a century ago, Richard Feynman was already aware that there is still much scope on the backside [3], and he urged his audience to start a second branch of physics. The study focus changed from the microstate to the nano state—technology aids in developing strategies or systems that accomplish required duties compellingly and. Nanotechnology is the science and engineering of creating microscopic materials at the nanoscale for specific uses. Nanotechnology was first developed in the 1979s. [4,5], and tremendous growth and discoveries in the "nanoworld" accompanied regular consequences in a Nobel Prize for the respective scientists. According to Mihail (Mike) Roco of the "US National Nanotechnology Initiative's generation technology development chart," we have already entered the fourth generation stage, in which molecular devices will be the dominant nanotechnology [6].

## MATERIAL & METHODS

### "COLLECTION OF PLANTS"

The leaves of the "Shafallah tree" or known as the Devil's tree, *A.scholaris*, are obtained from different places in central and southern Iraq. The leaves, plant life, and fruits are washed several times with deionized water to remove the sticky texture, then dried in the shade for 5–6 weeks at room temperature before being pulverized with a household blender. For the manufacture of plant extracts, the dry powder is stored in an airtight container.

### "PREPARATION OF PLANTS EXTRACTS"

To release intracellular chemicals into liquid, heat the mixture for 15 minutes at 60°C with constant stirring. The extracts were filtered using Whatman No. 1 filter paper, chilled to 4°C, and utilized to synthesize biogenic silver nanoparticles after cooling.  $\text{AgNO}_3$  was stabilized and lowered by extracts of several flora components.

### "Synthesis of Biogenic Silver Nanoparticles"

10 mL of *A. scholaris* "leaves, foliage, and fruits" plant component extracts are given one by one to a 250 mL conical flask containing 100 mL 5mM silver nitrate solution. The  $\text{AgNO}_3$  solution is originally whitish in color, but after being swirled constantly for 30 to 60 minutes at room temperature (30°C). The hue changes from whitish to brownish orange, visibly confirming the creation of biogenic silver nanoparticles. Centrifugation of synthesized nanoparticles results in the production of a pellet. Separate biogenic AgNP pellets have been cleaned with distilled water and accumulated for comparative testing [7].

### "Optimization Of Factors For Synthesized Biogenic Silver Nanoparticles"

#### "Effect of pH"

The response pH of various manufactured biogenic AgNPs has been tuned at specific pH levels, with 3, 5, 7, 9, and eleven being the most common. A spectrophotometer was used to test the absorbance of the produced AgNPs at a certain pH [8]. The "pH of the response was previously adjusted with 0.1 N HCl and 0.1 N NaOH".

#### "Effect of Temperature"

"The temperatures of several manufactured biogenic AgNPs were tuned at a single temperature, with the response temperature measured from 10 to 60 degrees Celsius". A spectrophotometer was used to determine the absorbance of the produced AgNPs at a given temperature [8].

#### "Effect of Time"

At varying time intervals, the times of various produced biogenic AgNPs were tuned. From 0 to 24 hours, the response time was measured. A spectrophotometer was used to test the absorbance of the produced AgNPs at various time intervals [8].

#### "Effect of Reactant Concentration"

To improve the concentration ratio of plant extracts, we used "5 mL, 10 mL, 15 M, 20 M, and 25 M" of plant extracts in the 1 M silver nitrate solution to increase the concentrations of leaves, flowers, and fruits. Tests on the absorbance of the generated AgNPs at varied concentrations of leaves, flowers, and fruits extracts were performed using a spectrophotometer[8].

### "Effect of Concentration of Metal Ion"

The response to one-of-a-kind quantities of silver nitrate used to be optimized for the production of AgNPs, with the response maintained at 1 mM, three mM, five mM, and seven mM. The absorbance of the produced AgNPs was measured using a spectrophotometer with complete knowledge of AgNO<sub>3</sub> [8].

### "Characterization of biogenic silver nanoparticles"

#### "UV-visible spectrophotometer"

Ingestion spectroscopy in the UV-Visible region has long been an essential tool for nanoparticle representation. The formation of biogenic AgNPs and bio rebate of Ag<sup>+</sup> particles in the arrangement is monitored using UV-Visible retention Spectroscopy "Systronic 2203 UV Vis" in the region of 300- 500 nm, which provides the result of floor plasmon reverberation molded for steel. This floor plasmon reverberation is caused by the sound wavering of free conduction electrons attracted by light [9].

### "Particle Size And Zeta Potential Determination"

First, the hydrodynamic response of the nanoparticles is weakened by the addition of NaCl as a suspending electrolyte in two-fold-refined water "50 mL" "2 x10<sup>-2</sup> M NaCl". The needed pH cost is modified at that moment. For the better part of a half-hour, the samples are tossed around. After 30 minutes, the pH balance and the zeta conceivable of the silver nanoparticles are evaluated. Afterward, Molecule sizes (z-normal), polydispersity lists (PI), and zeta potentials of silver nanoparticles are examined at 25 C of integrated biogenic AgNPs with an unbiased molecule size/Zeta reasonable analyzer. In addition, the stability of

choreographed AgNPs is tested using this evaluation. [10].

#### "Electron Microscopy/ Selected Area Electron Diffraction (SAED) Analysis"

Transmission electron microscopy is used initially to determine the shape and size of AgNPs. AgNP pattern is then applied on the copper grid with thin copper and holey carbon disc and dries in vacuo after one drop is applied. After washing and diluting the stable biogenic AgNPs, the absorbance range of 0.5 is achieved. AgNPs generated using Tecnai G2 FEI High-Resolution Transmission Electron Microscope operating at 200 kV of acceleration were seen with this microscope. Additional samples of SAED were collected at a previous time.

#### "Fourier Transform Infrared (FT-IR) Spectroscopic Studies"

The FT-IR technique analyzes the evidence of natural practical groupings responsible for reducing metal particles to metal nanoparticles. Fourier Transform Infrared spectroscopy is used to analyze the spectra of the powdered AgNPs structure. The samples are prepared by sprinkling the AgNPs in a dry KBr vehicle and sprinkling them on a simple plate. KBr is used as a standard for the evaluation of tests.

#### "Powder X-Ray Diffraction (XRD) Studies"

"X-beam diffraction estimations were done for the bio-reduced silver metal arrangement."

#### "Determination of Antituberculosis Activity By LJ Slope Method"

Lowenstein Jensen (L J) Slope method was used to determine this. H37Rv [Acid Fast Bacilli] MTCC 200 was used to verify the results. Development and weakening were accomplished by using L J (Lowenstein Jensen) medium. The strain used in testing was

accustomed to a 1mg/ml inoculum size. The use of a screening test for assurance of antimycobacterial activity on the Lowenstein Jensen (LJ) medium is dependent on whether or not bacterial suitability balance is maintained. The development was emulsified in 3 ml of clean 0.9 percent saline, and the turbidity was adjusted to 0.5 using a densimeter. In a Bio-wellbeing hood, 0.5 ml of this slurry was dispersed aseptically into two sterile cylinders. A DMSO solution containing 0.5 ml of biogenic silver nanoparticles and 0.5 ml of DMSO was added to the control tubes. For this experiment, 37 degrees Celsius was the ideal temperature for vortexed cylinders to hatch out.

For the purpose of determining the Minimum Inhibitory Concentration (MIC) of various medicines, the following methods were used: The main screen is seen here. The combined drugs were administered at 500 g/ml, 250 g/ml, and 125 g/ml during the screening process. The dynamically integrated drugs discovered in this crucial screening were also tested in a dual setup of weakening against all bacteria.

"The medications observed dynamic in essential screening were likewise weakened to acquire 100 µg/ml, 50 µg/ml, 25 µg/ml, 12.5 µg/ml, 6.250 µg/ml, 3.125 µg/ml and 1.5625 µg/ml fixations.

This strategy followed biogenic AgNPs incorporated utilizing *A. scholaris* (leaves, blossoms, and organic products) removes and 5mM silver nitrate arrangement as a test, standard antitubercular drugs Rifampicin and Isoniazid are utilized as a positive control" [11-14].

## RESULTS & DISCUSSION

### "SYNTHESIS OF BIOGENIC SILVER NANOPARTICLES"

The green amalgamation of silver nanoparticles through pre-arranged diverse plant components has been finished, removing them from the solution. Written, silver nanoparticle arrangement seems dull brown or black. The shift in color from colorless to brownish orange to black reflects the production of AgNPs after adding *A. scholaris* leaf extracts to AgNO<sub>3</sub> solution. The other six plants and their components extracted (*A. marmelos* leaf, *A. marmelos* fruit, *A. scholaris* leaf color changed to dark brown to following blackish treatment with AgNO<sub>3</sub>) had the same result. Nanoparticles have a feature known as a quantum restriction, which affects the optical properties of nanoparticles by limiting their size. This reduced aqueous component is employed for additional characterizations. This proves that the synthesis of AgNPs processes has begun. AgNPs' color intensity rises as incubation time increases, as described above.

#### "Optimization of Synthesized Biogenic Silver Nanoparticles"

"For the synthesis of AgNPs, different parameters were optimized, i.e., pH, temperature, time, reactant concentration (Plant extract), the concentration of metal ion" (AgNO<sub>3</sub>).

##### "Effect of pH"

After the plant extract was added to the AgNO<sub>3</sub> solution at pH 7, the reaction was sped up, and the formation was noticed within 30 minutes. Biogenic AgNPs are formed when a colorless solution changes to a brownish color. A UV absorption peak provided further proof of AgNP production. At pH 2 and 5, which are both acidic, no particles are formed.

##### "Effect of Temperature"

UV absorbance spectra of biogenic AgNPs at different temperatures "15, 30, and 60" show

that the sharpness of the peak is enhanced with the reduction in the NPs' size. The aggregation of particles at higher temperatures led to an increase in size after reaching the optimal temperature. A decrease in AgNP aggregation caused the first shrinkage. At 15°C, the reaction rate is slower, and the size of the particles is more significant.

##### "Effect of Time"

It is also explored how reaction time affected the combination of biogenic AgNPs. As the reaction time increased, more NPs were framed by UV absorbance spectra, and the apex became more refined. The synthesis of NPs began within 30 minutes, and the number of NPS grew steadily until the optimal limit was reached, at which point the size of the NPS rose somewhat.

##### "Effect of Reactant Concentration"

Variations in the concentration ratios of leaf extract to AgNO<sub>3</sub> are also investigated to maximize the generation of biogenic AgNPs while minimizing their size. In order to determine the optimal volume of plant extracts for increased synthesis of biogenic AgNPs, the quantities of plant extracts are changed from 5, 10, 15, 20, 25 mL.

##### "Effect of Concentration of Metal Ion"

All other parameters are maintained constant in order to enhance the formation of biogenic AgNPs. Using the UV-visible absorption spectra, a 1 mM to 3 mM solution of AgNO<sub>3</sub> resulted in a slow pace and a feeble absorption peak for the synthesis of AgNPs. However, it is interesting to note that this permits the fast creation of biogenic nanoparticles. Particles begin to clump together at a concentration of 7 mM, which reduces the absorption peak.

### "Dynamic Light Scattering Analysis and Zeta-Potential Measurements"

"Microtrac). There are many different ways to disperse laser diffraction technology in this operation. Following ultrasonication, the pre-arranged example is dispersed in deionized water. Sifting and centrifugation at 25°C at 5000 rpm for 15 seconds are then carried out, after which the supernatant has been collected. A PC-controlled molecule size analyzer is used to examine the distribution of molecules in the fluid after the supernatant was diluted 4 to numerous times. The zeta potential of the silver nanoparticles is used to determine the surface capabilities of the colloidal solution.

### "Particle Size Measurements"

Data regarding the size of colloidal silver nanoparticles and their granulometric circulation may be obtained from the number of molecules and their associated volume. Particles with polydispersity are found to be present in the nanoparticles examined by molecular size analysis. Underneath is where it is at. AgNPs mixed with different fixation

AgNO<sub>3</sub> "1mM, 3mM, 5mM, and 7mM" are found to be within the range of 0.7-100nm in molecular size analyzer. Consequently, the AgNPs paired with a 5mM AgNO<sub>3</sub> arrangement resulted in the least typical tight particle size compared to other AgNPs.

### "Zeta Potential Measurement"

The colloidal suspension's zeta potential is used to determine the safety of the colloidal particles. Stable silver nanoparticles must have a zeta potential of at least +30mV and - 30mV. The zeta esteems of the nanoparticles derived from six plants, and their various components (leaves, blooms, and organic products) were determined and presented in the table below with a maximum force of 100%. One of the primary reasons for delivering molecules with a limited size appropriation file is that these properties enable nanoparticles to be fully adjusted [15-17]. Six plants and a wide range of plant components (leaves, flowers, organic compounds) produced silver nanoparticles that had a negative charge and were stable at ambient temperature.

"Plant sample"	"Concentration of AgNO <sub>3</sub> (mM)"	"Average size (nm)"	"Zeta Potential (mV)"	"PDI"	"Polarity"
"A. scholaris leaf"	"1.0"	"34.3"	"18.92"	"0.235"	"Positive"
	"3.0"	"27.6"	"20.19"	"0.273"	"Positive"
	"5.0"	"14.7"	"19.77"	"0.318"	"Negative"
	"7.0"	"52.6"	"18.56"	"0.581"	"Negative"


### "Electron Microscopy/ Selected Area Electron Diffraction (SAED) Analysis"

The integrated biogenic silver nanoparticles are examined using TEM to determine their size and shape. A close look at the HR-TEM image of the integrated AgNPs in the plant and its

many parts, as seen in Figure, reveals the precise measurements, shapes, and sizes that the nanoparticles have taken. AgNPs, which are hexagonal and regularly circulated, are orchestrated by these plant extracts. Ten to fifty nanometers (nm) was the range of the

combined biogenic AgNPs. As seen in the SAED example, AgNPs are transparent [18-20].


### "Figure 1: SEM of Plant Extracts"



### "Fourier Transform Infrared (FT-IR) Spectroscopic Studies"

Plant extracts "identify the functional groups responsible for synthesizing silver nanoparticles from silver nitrate using FT-IR." Different biomolecules are responsible for decreasing, correcting, and covering up AgNPs orderly as diverse biomolecules choreograph them. The plant extracts' biogenic union with silver nanoparticles is determined using FTIR ranges.

### "Figure 2: FT-IR Spectra of plant extract"




### "Powder X-Ray Diffraction (XRD) Studies"

The biogenic silver nanoparticles' phase distribution, purity, and crystalline shape have been verified using X-ray diffraction (XRD) analysis. According to this formula, these biogenic AgNPs synthesized by plant extract have an average crystal size of between 1 and 10 nm. Below, you can see the XRD patterns of *A. scholaris* plants "leaves, flowers, and fruits [21,22]."

JCPDS No. 04-0783 is utilized as a reference to assign many distinct peaks of all synthesized biogenic AgNPs to this in the range of 0 to 80; it advocated the monophasic nature of synthesized AgNPs based on this data set [23,24].

**Figure 3: X-ray Diffraction of extract of plant**




"Antibacterial Activity of Biogenic Silver Nanoparticles"

"Zone of Inhibition in Bacteria"

The antibacterial activity of AgNPs derived from plant extracts is shown to be outstanding against both Gram-positive and Gram-negative bacteria. AgNPs synthesized using a modified Kirby Bauer diffusion method were tested against a wide range of bacterial strains, including *Staphylococcus aureus*, *Bacillus subtilis*, *Bacillus megaterium* "representatives of gram-positive bacteria," *Salmonella abony*, *Escherichia coli*, *Pseudomonas aeruginosa*, *Proteus Vulgaris*, and *Enterobacteriaceae* "representative of gram-negative bacteria." MTCC provided these seeds to us "Microbial Type Culture Collection." Several antibiotic-resistant microorganisms, including *Staphylococcus aureus* and *Escherichia coli*, were also examined. For each microbe, the gram staining data are shown below.

**"Figure 60 Gram staining images of (A) *B. subtilis*, (B) *B. megaterium* (C) *S. aureus*"**



## CONCLUSION

Ag's antibacterial properties are attributed to its positive charge, according to research. On Gram-negative bacteria, the antibacterial action of biogenic AgNPs is dependent on the concentration of AgNPs. Pits occur in the bacterial cell wall, and AgNPs accumulate there, reducing the membrane's permeability and ultimately leading to cell death. The membrane is damaged by free radicals produced by surface Ag NPs.

## Acknowledgment:

We, the authors, thank Phi-Nanotechnology Laboratories center and / Baghdad, and especially thank Prof. Dr. Majid Jaber, and Dr. Taha Mohsen Rashid for their help in carrying out nanoworks for plant extract particles in their laboratories also thanks for Dr. Karema



Zaidin khlaf from college of Science, University of Basrah, Iraq for their help in carrying out Biological activity.

## Reference

- J. Su, M. Gherasimova, G. Cui, H. Tsukamoto, J. Han, T. Onuma, M. Kurimoto, S.F.
- Chichibu, C. Broadbridge and Y. He, A.V. Nurmikko, Appl. Phys. Lett., 2009, 87, 183108.
- T. Vogel, J. de Boor, J. V. Wittemann, S. L. Mensah, P. Werner and V. Schmidt, Cryst. Growth Design, 2011, 11, 1896.
- K. Akamatsu, K. Nakashahi, S. Ikeda and H. Nawafune, Eur. Phys. J. D. 2003, 24, 377
- M. Lieberthal and W. D. Kaplan: Mater. Sci. Engg. A, 2001, 302, 83.
- T. Okada and J. Suehiro, Appl. Surf. Sci., 2007, 253, 7840.
- U. Backman, U. Tapper, J. K. Jokiniemi, Synthetic Metals, 2004, 142, 169.
- Cerchiara, T.; Luppi, B.; Chidichinao, G.; Bigucci, F.; Zecchi, V.; European Journal of Pharmaceutics and Biopharmaceutics 2005, 61, 195–200.
- Sharma, N. C.; Galatians, H. J.; Qaquis, J.; Galatians, A.; Rustogi, K. N.; Petrone, M. E.; Chaln, P.; Garcia, L.; Volpe, A. R.; Proskin, H. M. J Clin Dent 1999, 10, 131.
- Arbo's, P.; Wirth, M.; Goa, M. A.; Gabor, F.; Irache, J. M. J. Controlled Release 2002, 83, 321.
- Arbo's, P.; Campanero, M. A.; Arango, M. A.; Renedo, M. J.; Irache, J. M. J Controlled Release 2003, 89, 19.
- Lu, L.; Kobayashi, A.; Kikkawa, Y.; Tawa, K.; Ozaki, Y. J. Phys. Chem. B 2006, 110, 23234-23241.
- Bhattacharjee, R. R.; Chakraborty, M.; Mandal, T. K. J Phys Chem B 2006, 110, 6768.
- Shervani, Z.; Ikushima, Y.; Sato, M.; Kawanami, H.; Hakuta, Y.; Yokoyama, T.; Nagase, T.; Kuneida, H.; Aramaki, K. Colloid Polym Sci 2008, 286, 403.
- Wei, G. -T.; Yang, Z.; Lee, C. -Y.; Yang, H. -Y.; Wang, C. R. C. J. Am. Chem. Soc.2004, 126, 5036.
- Huang, S.; Ma, H.; Zhang, X.; Yong, F.; Feng, X.; Pan, W.; Wang, X.; Wang, Y.;
- Chen, S. J. Phys. Chem. B 2005, 109, 19823.
- Alaa G. Al-Hashimia1 , Sinan J. Abdul-Abbas1 , Najla Hussen Saper Al Garory1 , Shaker A. N. AL-Jadaan2 , H. N. K. Al-Salman, Isolation and diagnosis of phytochemicals extracted from pomegranate husks and study of the biological effect of extract (O-Veratramide) as an antimicrobial activity, International Journal of Green Pharmacy, Oct-Dec 2018, 12 (4), 310-321.
- H. N. K. AL-Salman , Shaker.A.N.AL-Jadaan, Estimation of Cortisone Acetate in Pharmaceutical Anti-inflammatory Drugs by HPLC-UV Technique, International Journal of Science and Research, 6 (2), 2017, 1178-1183.
- HNK. AL-Salman, Ekhlas Qanber Jasim, Hussein H. Hussein, Falah Hassan Shari, Theophylline Determination in Pharmaceuticals Using a Novel High-performance Liquid Chromatographic Process, NeuroQuantology, July 2021,19(7), 196-208 | doi: 10.14704/nq.2021.19.7.NQ21103.
- AL-Salman HN, Ali ET, Almukhtar OA, Jabir MS. 2-benzhydrylsulfinyl-N-hydroxyacetamide Extracted from Fig: A good Therapeutic Agent against Staphylococcus Aureus. AIP Conference Proceedings 2020; 2213(1): 020223-5.

- Al-Salman HNK, Ali ET, Jabir M, Sulaiman GM, Al-Jadaan SAS. 2-Benzhydrylsulfinyl-N-hydroxyacetamide-Na extracted from fig as a novel cytotoxic and apoptosis inducer in SKOV-3 and AMJ-13 cell lines via P53 and caspase-8 pathway. *European Food Research and Technology* 2020; 246(8): 1-18.
- Alassadi EAS, Jasim EQ, AL-Salman HNK, Mosa MN. Comparative Study of an In Vitro Release Patterns of Ceftaroline Fosamil from Chemically – Prepared Coated Hydroxyapatite Nanoparticles. *Systematic Reviews in Pharmacy* 2020; 11(3): 797- 805.
- Abd-Alrassol KS, AL-Salman HNK, Jasim EQ, Hussein HH. Determination and Evaluation of Doses of Metronidazole in Different Quantities and Formulations with Multiple Spectroscopic Methods. *Systematic Reviews in Pharmacy* 2020; 11(5): 130-139.
- OUDAH KH, HAMMOODI HA, Mazin AA. The effect of green tea extract and metformin on diabetic mellitus induce in male rats. *Iranian Journal of Ichthyology*. 2021 Aug 26;8:163-7.
- Oudah KH, Najm MA, Roomi AB, Al-sa HA. The recent progress of sulfonamide in medicinal chemistry. *Systematic Reviews in Pharmacy*. 2020;11(12):1473-7.
- Mokhtar, A. R. R. A. S. . (2022). Development Of Saponin Based Wettable Powder Formulation from *Phaleria macrocarpa* To Control *Pomacea maculate*. *Journal Of Advanced Zoology*, 43(1), 17–31. Retrieved from <http://jazindia.com/index.php/jaz/article/view/111>
- Anis S Mokhtar\*, Nurhayo Asib, A. R. R. . R. M. A. . (2022). Development of Saponin based Nano emulsion formulations from *Phaleria macrocarpa* to Control *Aphis gossypii*. *Journal Of Advanced Zoology*, 43(1), 43–55. Retrieved from <http://jazindia.com/index.php/jaz/article/view/113>